


# Effect of nano $Y_2O_3$ dispersion on thermal, microstructure, mechanical and high temperature oxidation behavior of mechanically alloyed W-Ni-Mo-Ti

A. Patra, R.R. Sahoo, S.K. Karak, S.K. Sahoo  
Metallurgical and Materials Engineering Department



The present research deals with the fabrication of mechanically alloyed W based alloys with nominal composition of  $W_{75}Ni_{10}Mo_{10}Ti_5$  (alloy A),  $W_{74}Ni_{10}Mo_{10}Ti_5(Y_2O_3)_1$  (alloy B),  $W_{73}Ni_{10}Mo_{10}Ti_5(Y_2O_3)_2$  (alloy C) (all in wt.%) by compaction at 500 MPa pressure for 5 min and conventional pressureless Ar injected sintering at  $1500^\circ C$  for 2 h. The phase evolution, microstructure, thermal characteristics, mechanical and high temperature behavior of the mechanically alloyed powders and sintered alloys has been studied by X-ray diffraction (XRD), Scanning electron microscopy (SEM), High resolution transmission electron microscopy (HRTEM), Energy dispersive spectroscopy (EDS) and Differential scanning calorimetry (DSC). Alloy C shows minimum crystallite size and maximum lattice strain, dislocation density of 18.6 nm, 0.54%,  $36.71 \times 10^{16}/m^2$  respectively at 20 h of milling as compared to other alloys. The activation energy for recrystallization decreases with increase in  $Y_2O_3$  dispersion. The residual stress also enhances with increased  $Y_2O_3$  content. Alloy C exhibits improved relative sintered density, hardness and elongation of 92.1%, 7.22 GPa, 12.73% respectively and appreciable wear resistance, high temperature oxidation resistance at  $1000^\circ C$  whereas maximum compressive strength of 1.91 GPa has been recorded in alloy B as compared to other alloys. Most interestingly the ductility also enhances with increase in  $Y_2O_3$  dispersion. **More in International Journal of Refractory Metals and Hard Materials. DOI: 10.1016/j.ijrmhm.2017.09.015**